

BARRIERESCHRUMPFBEUTEL ASB
BARRIER SHRINK BAG ASB

Eigenschaften <i>Properties</i>	Einheit <i>Unit</i>	Werte <i>Data</i>	Werte <i>Data</i>	Testmethode <i>Test method</i>
Beuteltype <i>Bag type</i>		ASB 60	ASB 80	
Foliendicke <i>Thickness</i>	MY	55	75	DIN 53370 23°C / 50% r.h.
Schrumpfeigenschaften <i>Shrinkage</i>				
längs <i>Lengthwise</i>	%	43	43	DIN EN ISO 2286-2 93°C
quer <i>Transverse</i>	%	55	55	DIN EN ISO 2286-2 93°C
Durchlässigkeiten <i>Permeability</i>				
Wasserdampf <i>Water vapour</i>	g/m ² d	<1	<1	DIN 53122 23°C / 50% r.h.
Sauerstoff (O ₂) <i>Oxygen (O₂)</i>	cm ³ /m ² bar	12	12	DIN 53380 23°C / 0% r.h.
Sauerstoff (O ₂) <i>Oxygen (O₂)</i>	cm ³ /m ² bar	12	12	DIN 53380 23°C / 85% r.h.
Kohlendioxid (CO ₂) <i>Carbon dioxide (CO₂)</i>	cm ³ /m ² bar	40	40	DIN 53122 23°C / 0% r.h.
Allgemeine Informationen <i>General Information</i>				
Siegeltemperatur <i>Sealing temperature</i>	°C	130 - 180	130 - 180	
Empfohlene Lagerbedingung <i>Recommend storage conditions</i>	°C % r.h.	+12 - +20 40 - 60	+12 - +20 40 - 60	
Maximale Lagertemperatur <i>Maximum storage conditions</i>	°C	+25	+25	
Empfohlene Lagerdauer <i>Recommend storage time</i>	Jahre year	<1	<1	

Die vorstehend gemachten Angaben sind ca. Werte für unverformte Folien und Beutel und basieren auf unseren derzeitigen Kenntnissen und Erfahrungen. Eine rechtlich verbindliche Zusicherung bestimmter Eigenschaften oder Eignung für einen konkreten Einzelfall kann aus unseren Angaben nicht abgeleitet werden. Nach dem Gesetz obliegt die technische und sensorische Eignung für den vorgesehenen Verwendungszweck dem Verwender.

All information given on this datasheet is approximated values, correct to the best of our knowledge and relates to unformed film only. A legally binding assurance of certain qualities or suitability for a concrete individual case cannot be derived from our statements. According to the law, the technical suitability and organoleptic test for the intended use is incumbent on the user.